

Test Report

No.: SZTYR061033512/LP

Date: OCT 18, 2006

Page 1 of 2

SWIFTECH COMPANY LTD.
BLOCK 6, ZHONGSHAN CIVIL
SCIENCE & TECHNOLOGY PARK,
ZHONGSHAN CITY, GUANGDONG

Report on the submitted samples said to be 9017, CASTLE BOUNCER WITH SLIDE

Style / Item No. : 9017
Sample Receiving Date : SEP 29, 2006
Testing Period : SEP 30, 2006 TO OCT 18, 2006


Test Requested : To determine the Cadmium Content in the submitted samples in accordance with the EEC Directive 91/338/EEC.

Test Method : With reference to EN1122: 2001 method B / Other acid digestion.
Analysis was performed by Atomic Absorption Spectrometer.

Results : Please refer to next page(s).

Conclusion : When tested as specified, the submitted samples comply with the Total Cadmium Requirement of the EEC Directive 91/338/EEC.

Signed for and on behalf of
SGS-CSTC Ltd.



Li Ying, Susan
Section Manager

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.



SZL 570404

Test Report

No.: SZTYR061033512/LP

Date: OCT 18, 2006

Page 2 of 2

Results:

	1	2	3	4	5	6	7	Limit
Cadmium Content	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	100 ppm
	8	9	10	11	12	13	14	Limit
Cadmium Content	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	100 ppm
	15	16	17	18	19	20		Limit
Cadmium Content	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.		100 ppm
	21	22	23	24	25	26		Limit
Cadmium Content	N.D.	5	N.D.	14	N.D.	23		100 ppm

Specimen Description:

1. Red fabric w/ white plastic sheet backing (Bouncer)
2. Yellow fabric w/ white plastic sheet backing (Bouncer)
3. Blue fabric w/ white plastic sheet backing (Bouncer)
4. Yellow cord
5. Black netting
6. Yellow plastics (Nail)
7. Yellow fabric
8. White fabric sewn-in label
9. Red woven band
10. Dk. blue plastic sheet (Bouncer)
11. Red velcro
12. Black woven (Binding)
13. Black coating
14. Green coating
15. Yellow coating
16. Blue fabric w/ grey plastic sheet backing (Repair patch)
17. Transparent plastic sheet w/ adhesive backing (Repair patch)
18. Red coating
19. Blue coating
20. Green plastic sheet (Bouncer)
21. Red woven (Binding)
22. Dull yellow fabric w/ white plastic sheet backing
23. White fabric (Ling)
24. Lt. blue fabric w/ blue plastic sheet backing
25. White surfaced brown corrugated paper board (Box)
26. Brown fabric w/ grey plastic sheet backing (Bouncer)

Note : - ppm = mg/kg
 - N.D. = Not Detected (< 5 ppm)
 - Results shown are of the total weight of dry samples.

*** End of Report ***

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 day only. This Test Report shall not be reproduced except in full, without written approval of the Company.



SZL 570405